



DISTACCANTE

Coloured release agent for decorative stamped concrete flooring



konstruktive · **leidenschaft**



Strada Spartafino, 2
12016 Peveragno (CN)



ph. +39 0171 38.38.00
Fax +39 0171 33.93.95



info@vimark.com
www.vimark.com



PRODUCT DESCRIPTION

DISTACCANTE is a powdered release agent that is water-repellent and coloured, specific for decorative stamped flooring. The product enhances the texture and facilitates stamp tool separation from fresh and previously dusted concrete.

DISTACCANTE adds variegated colour to the imprint, and can increase the perceived depth of stamp patterns. The product is applied with the dry-shake method on freshly cast concrete with **STAMPOCEM**, distributing manually the anhydrous product and repeating if needed. **DISTACCANTE** is the second step in preparing a decorative stamped concrete flooring.

COMPOSITION

DISTACCANTE is a specially formulated premixed powder, consisting of special release agents, binders and inorganic pigments.

APPLICATION

DISTACCANTE is applied in the procedure of stamped concrete decoration on the first dry-shake layer of **STAMPOCEM** immediately before the stamp tool phase. Apply the product manually with the dry-shake method evenly to the entire surface. Its application allows you to create a correct colour combination compared to other methods. On the **DISTACCANTE** layer during the plastic phase, imprint with stamp the chosen decorative designs. After curing of the stamped decorative floor (24-36 hours), wash the decorated surfaces with pressure washer and single brush floor cleaner.

The joints in the slabs must be carried out after 24 to 48 hours after laying the floor with a diamond disc cutter. The joints must be properly sealed.

Protect stamped decorative flooring by applying one or more coats of di **VIMAFLOOR S**.

INDICATIVE AMOUNTS REQUIRED

0.125-0.150 kg per m².

COLOUR

Collection: STAMPOCEM.colours

PACKAGING

7,5 kg tubs.

STORAGE

12 months in original intact packaging and stored in a dry place.

RECOMMENDATIONS

Do not apply on concrete during setting time.

Do not apply at temperatures below + 5°C or above + 35°C.

Apply after the first dry-shake application of **STAMPOCEM**.

Do not apply externally during rain or frost.

Do not apply externally with strong wind, direct sunlight or temperatures above + 35°C.

During the manual application use appropriate personal protection.

PRODUCT DATA

Appearance	powder	
Colour	coloured	
Powder volume mass	~ 550 kg/m ³	EN 1015-10
Maximum aggregate size	≤ 0.20 mm	





APPLICATION DATA

<i>Min. temperature for application</i>	+ 5°C
<i>Max. temperature for application</i>	+ 35°C
<i>Fit for walking on</i>	> 12 hours

REMARKS

Product for professional use. The data and instructions in this data sheet are based on our best practical and laboratory experience. They refer to laboratory tests and should be considered indicative. In view of the different conditions of use and application, which depend on factors over which Vimark has no control (type of surface, environmental conditions, technical indications for fixing, etc.), those who use the product are responsible for ascertaining whether or not it is suitable for the intended purpose. Thus our warranty obligation merely covers the quality and fade-free characteristics of the actual product, and exclusively in relation to the aforementioned data. Vimark reserves the right to make technical modifications without prior notice. This technical data sheet voids and substitutes all previous editions. Updates will be published on the web site www.vimark.com.

